

<b>Prüfbericht - Nr.:</b> <i>Test Report No.:</i>		IND/BLR/CH/2019/7014	<b>Seite 1 von 5</b> <i>Page 1 of 5</i>		
<b>Auftraggeber:</b> <i>Client:</i>		<b>SUNFLEX RECYCLING PVT LTD</b> Plot no 274/4, Opposite Gujarat High court, B/h Satyamev Complex, Sg highway, sola 380060 India			
<b>Gegenstand der Prüfung:</b> <i>Test item:</i>		Crumb Rubber			
<b>Bezeichnung:</b> <i>Identification:</i>		-	<b>Serien-Nr.:</b> <i>Serial No./ Document Submitted:</i>	TRF Date : 31.08.2019	
<b>Wareneingangs-Nr.:</b> <i>Receipt No.:</i>		03092019	<b>Eingangsdatum:</b> <i>Date of receipt:</i>	03.09.2019	
<b>Order No.:</b>		166173813	<b>Testing Period:</b>	03.09.2019 to 20.09.2019	
<b>Prüfport:</b> <i>Testing location:</i>		TÜV Rheinland India Pvt Ltd, Plot No.27B, 2nd cross Electronic City Phase I Bangalore - 560 100, Karnataka, India.			
<b>Prüfgrundlage:</b> <i>Test Parameters:</i>		Customer's Requirement: Particle Size Distribution.			
<b>Prüfergebnis:</b> <i>Test Result:</i>		Refer Page No.2 to 2			
<b>Prüflaboratorium/ Testing Laboratory:</b>					
<b>zusammengestellt/ compiled by:</b>			<b>kontrolliert/ checked by:</b>		
20.09.2019 Vijetha CSE, Material Testing Laboratories, Industry Services			20.09.2019 Rajesh Jain B Technical Head, Material Testing Laboratories, Industry Services		
<b>Datum</b> <i>Date</i>	<b>Name</b> <i>Name</i>	<b>Unterschrift</b> <i>Signature</i>	<b>Datum</b> <i>Date</i>	<b>Name</b> <i>Name</i>	<b>Unterschrift</b> <i>Signature</i>
<b>Sonstiges/ Other Aspects: NIL</b>					
<b>Abkürzungen:</b>		<i>ok / P = entspricht Prüfgrundlage</i>	<b>Abbreviations:</b>		<i>ok / P = passed</i>
		<i>fail / F = entspricht nicht Prüfgrundlage</i>			<i>fail / F = failed</i>
		<i>n.a. / N = nicht anwendbar</i>			<i>n.a. / N = not applicable</i>
<b>Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.</b>					
<i>This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. Test item submitted by client. Sampling not done by TUVRI</i>					

### TEST RESULTS

Sample Description	Crumb rubber
Sampling : 1. Submitted Sample drawn by the laboratory : No (If yes please provide the sampling reference)	

**1. Particle Size Distribution:**

Sl. No	Test / Parameter	Unit	Result	Test Method
1	Particle Size below 10%	microns	206.590	Malvern Mastersizer 2000
	Particle Size below 50%	microns	360.039	
	Particle Size below 90%	microns	578.059	
	Particle Size below 99%	microns	756.449	
	Average Particle Size	microns	360.039	

Note:  
 Data & Chromatogram is attached as Annexures  
 Range of analysis for Particle Size Distribution 0.02 to 2000 microns


## Analysis

**Particle Name** Particle  
**Particle Refractive Index** 1.900  
**Particle Absorption Index** 1.000  
**Dispersant Name** Dry dispersion  
**Dispersant Refractive Index** 1.000  
**Scattering Model** Mie  
**Analysis Model** General Purpose  
**Laser Obscuration** 0.71 %

## Result

**Concentration** 0.0271 %  
**Span** 1.045  
**Uniformity** 0.326  
**Specific Surface Area** 19.37 m<sup>2</sup>/kg  
**D [3,2]** 295.051 µm  
**D [4,3]** 367.076 µm  
**Dv (10)** 198.880 µm  
**Dv (20)** 244.975 µm  
**Dv (50)** 351.303 µm  
**Dv (90)** 566.014 µm  
**Dv (95)** 633.672 µm  
**Dv (100)** 859.166 µm  
**Volume Below (10) µm** 0.00 %  
**Volume Below (20) µm** 0.00 %

## Frequency (compatible)



## Result

Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under
0.010	0.00	0.060	0.00	0.357	0.00	2.131	0.00	12.726	0.00	76.006	1.70	453.960	74.45
0.011	0.00	0.068	0.00	0.405	0.00	2.421	0.00	14.458	0.00	86.355	2.07	515.772	84.50
0.013	0.00	0.077	0.00	0.460	0.00	2.750	0.00	16.427	0.00	98.114	2.37	586.001	92.05
0.015	0.00	0.088	0.00	0.523	0.00	3.125	0.00	18.664	0.00	111.473	2.60	665.793	96.86
0.017	0.00	0.100	0.00	0.594	0.00	3.550	0.00	21.205	0.00	126.652	2.92	756.449	99.26
0.019	0.00	0.113	0.00	0.675	0.00	4.034	0.00	24.092	0.00	143.897	3.58	859.450	100.00
0.022	0.00	0.128	0.00	0.767	0.00	4.583	0.00	27.373	0.00	163.490	5.00	976.475	100.00
0.024	0.00	0.146	0.00	0.872	0.00	5.207	0.00	31.100	0.00	185.752	7.65	1109.435	100.00
0.028	0.00	0.166	0.00	0.991	0.00	5.916	0.00	35.335	0.00	211.044	12.04	1260.499	100.00
0.032	0.00	0.188	0.00	1.125	0.00	6.722	0.00	40.146	0.08	239.780	18.53	1432.133	100.00
0.036	0.00	0.214	0.00	1.279	0.00	7.637	0.00	45.613	0.25	272.430	27.26	1627.136	100.00
0.041	0.00	0.243	0.00	1.453	0.00	8.677	0.00	51.823	0.50	309.525	37.99	1848.692	100.00
0.046	0.00	0.276	0.00	1.651	0.00	9.858	0.00	58.880	0.86	351.670	50.10	2100.416	100.00
0.053	0.00	0.314	0.00	1.875	0.00	11.201	0.00	66.897	1.27	399.555	62.63	2386.415	100.00


## Analysis

**Particle Name** Particle  
**Particle Refractive Index** 1.900  
**Particle Absorption Index** 1.000  
**Dispersant Name** Dry dispersion  
**Dispersant Refractive Index** 1.000  
**Scattering Model** Mie  
**Analysis Model** General Purpose  
**Laser Obscuration** 0.33 %

## Result

**Concentration** 0.0151 %  
**Span** 0.952  
**Uniformity** 0.293  
**Specific Surface Area** 15.96 m<sup>2</sup>/kg  
**D [3,2]** 357.936 µm  
**D [4,3]** 404.813 µm  
**Dv (10)** 237.901 µm  
**Dv (20)** 278.977 µm  
**Dv (50)** 384.311 µm  
**Dv (90)** 603.839 µm  
**Dv (95)** 668.903 µm  
**Dv (100)** 974.040 µm  
**Volume Below (10) µm** 0.00 %  
**Volume Below (20) µm** 0.00 %

## Frequency (compatible)



## Result


Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under
0.010	0.00	0.060	0.00	0.357	0.00	2.131	0.00	12.726	0.00	76.006	0.00	453.960	67.34	2711.357	100.00
0.011	0.00	0.068	0.00	0.405	0.00	2.421	0.00	14.458	0.00	86.355	0.00	515.772	79.16	3080.544	100.00
0.013	0.00	0.077	0.00	0.460	0.00	2.750	0.00	16.427	0.00	98.114	0.00	586.001	88.50	3500.000	100.00
0.015	0.00	0.088	0.00	0.523	0.00	3.125	0.00	18.664	0.00	111.473	0.00	665.793	94.87		
0.017	0.00	0.100	0.00	0.594	0.00	3.550	0.00	21.205	0.00	126.652	0.00	756.449	98.39		
0.019	0.00	0.113	0.00	0.675	0.00	4.034	0.00	24.092	0.00	143.897	0.07	850.450	99.76		
0.022	0.00	0.128	0.00	0.767	0.00	4.583	0.00	27.373	0.00	163.490	0.56	976.475	100.00		
0.024	0.00	0.146	0.00	0.872	0.00	5.207	0.00	31.100	0.00	185.752	2.03	1109.435	100.00		
0.028	0.00	0.166	0.00	0.991	0.00	5.916	0.00	35.335	0.00	211.044	5.09	1260.499	100.00		
0.032	0.00	0.188	0.00	1.125	0.00	6.722	0.00	40.146	0.00	239.780	10.32	1432.133	100.00		
0.036	0.00	0.214	0.00	1.279	0.00	7.637	0.00	45.613	0.00	272.430	18.09	1627.136	100.00		
0.041	0.00	0.243	0.00	1.453	0.00	8.677	0.00	51.823	0.00	309.525	28.37	1848.692	100.00		
0.046	0.00	0.276	0.00	1.651	0.00	9.858	0.00	58.880	0.00	351.670	40.68	2100.416	100.00		
0.053	0.00	0.314	0.00	1.875	0.00	11.201	0.00	66.897	0.00	399.555	54.08	2386.415	100.00		

**Analysis**

**Particle Name** Particle  
**Particle Refractive Index** 1.900  
**Particle Absorption Index** 1.000  
**Dispersant Name** Dry dispersion  
**Dispersant Refractive Index** 1.000  
**Scattering Model** Mie  
**Analysis Model** General Purpose  
**Laser Obscuration** 0.53 %

**Result**

**Concentration** 0.0212 %  
**Span** 1.005  
**Uniformity** 0.314  
**Specific Surface Area** 18.05 m<sup>2</sup>/kg  
**D [3,2]** 316.571 µm  
**D [4,3]** 382.886 µm  
**Dv (10)** 214.395 µm  
**Dv (20)** 258.121 µm  
**Dv (50)** 365.376 µm  
**Dv (90)** 581.771 µm  
**Dv (95)** 651.174 µm  
**Dv (100)** 971.982 µm  
**Volume Below (10) µm** 0.00 %  
**Volume Below (20) µm** 0.00 %

**Frequency (compatible)**

**Result**

Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under	Size (µm)	% Volume Under
0.010	0.00	0.060	0.00	0.387	0.00	2.131	0.00	12.726	0.00	76.006	1.11	451.960	71.39
0.011	0.00	0.068	0.00	0.405	0.00	2.421	0.00	14.458	0.00	86.355	1.36	515.772	82.17
0.013	0.00	0.077	0.00	0.460	0.00	2.790	0.00	16.427	0.00	98.114	1.55	586.001	90.47
0.015	0.00	0.088	0.00	0.523	0.00	3.125	0.00	18.664	0.00	111.473	1.69	665.793	95.95
0.017	0.00	0.100	0.00	0.594	0.00	3.550	0.00	21.205	0.00	126.652	1.86	756.449	98.85
0.019	0.00	0.113	0.00	0.675	0.00	4.034	0.00	24.092	0.00	143.897	2.27	859.450	99.88
0.022	0.00	0.128	0.00	0.767	0.00	4.583	0.00	27.373	0.00	163.490	3.00	976.475	100.00
0.024	0.00	0.146	0.00	0.872	0.00	5.207	0.00	31.100	0.00	185.752	5.45	1109.435	100.00
0.028	0.00	0.166	0.00	0.991	0.00	5.916	0.00	35.335	0.00	211.044	9.27	1260.999	100.00
0.032	0.00	0.188	0.00	1.125	0.00	6.722	0.00	40.146	0.05	239.780	15.21	1432.133	100.00
0.036	0.00	0.214	0.00	1.279	0.00	7.687	0.00	45.613	0.15	272.430	23.50	1627.136	100.00
0.041	0.00	0.243	0.00	1.453	0.00	8.677	0.00	51.823	0.32	309.525	34.00	1848.692	100.00
0.046	0.00	0.276	0.00	1.651	0.00	9.858	0.00	58.880	0.55	351.670	46.15	2100.416	100.00
0.053	0.00	0.314	0.00	1.875	0.00	11.201	0.00	66.897	0.83	399.555	59.00	2386.415	100.00

---- End of Test Report ----